



NIPPON GRAPHITE FIBER

GRANOC Prepreg <Low Modulus CF>

CF	Grade	F.A.W. (g/m ²)	RC (wt%)	T.A.W. (g/m ²)	Thickness mm	remark
XN-05	NG00550-540S	55	40	92	0.06	
	NG00750-437H	75	37	119	0.08	
	E052AA-10N	100	37	159	0.11	
	E0526A-12N	125	37	198	0.14	
XN-10	NTA0550-540S	55	40	92	0.06	
	NTA0750-437H	75	37	119	0.08	
	E1026A-09N	95	37	151	0.10	
	E1026C-10N	100	33	149	0.10	
	E1026D-12N	125	30	179	0.11	
	E1026C-15N	150	33	224	0.15	
XN-15	NU10550-539S	55	39	90	0.06	
	NL10750-437H	75	37	119	0.08	
	NL11000-437H	100	37	159	0.10	
	E1526C-10N	100	33	149	0.10	
	E1526D-12N	125	30	179	0.11	
	E1526C-15N	150	33	224	0.15	
	NL11500-437H	150	37	238	0.15	